

## 1. Introduction

HANWHA P-1000 is a PVC homopolymer made by suspension polymerization. It is recommended for various products such as pipe, sheet, profile, wire, film manufacturing. P-1000 is a general purpose resin used for soft and rigid applications and is most widely used in PVC grades.

## 2. Applications

Pipe, Window profile, Wire sheath, Soft/Rigid sheet & film, Hose, Leather, Wrap

## 3. Properties

Properties	Unit	Typical value	Methods
Degree of polymerization	-	1000±50	JIS K6720-2
K-Value	-	66	DIN 53726
Apparent bulk density	g/cm <sup>3</sup>	0.55±0.04	ASTM D1895
Volatility	%	Below 0.30	ASTM D3030
Sieve analysis (42mesh pass)	%	100	HSC method

※ The values given above are typical test results which should be used as a guide only. They do not form the whole or part of a specification or guarantee.

## 4. Storage, Packaging, Safety

### Storage

P-1000 should be stored dry conditions and at room temperature below 25°C.

## **Safety and Handling**

The Hanwha Solutions Corporation provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, use and transportation. Hanwha Solutions Corporation strongly encourage its customers to review MSDS on its products and other materials prior to their use. P-1000 is normally supplied as a powder in 25kg polypropylene inner coated paper bag, 600kg flecon bag as well as in bulk form.

P-1000 is not formulated to contain any hazardous or regulated materials such as lead, cadmium, mercury, and chromium compounds. And Hanwha Solutions Corporation guarantee that P-1000 does not include any hazardous or regulated materials during the manufacturing process

## **General Information**

The data and recommendations contained in this brochure represent the current state of our knowledge and serve as a guide only to our products and their potential applications. Therefore, no warranty of specific properties of the products mentioned herein nor of their suitability or fitness for a particular purpose is implied.

Further information and recommendations for processing can be obtained from our technical support staff and representatives.