

Polyvinyl Alcohol

References

Amuco Inc.
200 South Andrews Ave. Suite 200
Fort Lauderdale, FL 33301 USA.
Tel: +1(754)779 7867
sales@amucoinc.com
www.amucoinc.com

amuco.



Reference	Specifications					
	Alcoholysis Degree	Sodium Acetate	Volatile	Ash	PH Value	Viscosity
Polyvinyl Alcohol 17-99f (L)	99.0-99.9%	2.5 % max	5% max	0.7% max	5-7	28.0-32.0 mpa.s
Polyvinyl Alcohol 3-88 (L)	86.0-90.0%	2.5 % max	5% max	0.7% max	5-7	3.0-4.0 mpa.s
Polyvinyl Alcohol 4-88 (L)	6.0-90.0%(mol/mol)	2.5 % max	5% max	0.7% max	5-7	4.0-5.0 mpa.s
Polyvinyl Alcohol 4-99 (L)	98.0-99.5%	2.5 % max	5% max	0.7% max	5-7	4.0-5.0 mpa.s
Polyvinyl Alcohol 5-88 (L)	86.0-90.0%	2.5 % max	5% max	0.7% max	5-7	4.5-6.0 mpa.s
Polyvinyl Alcohol 5-99 (L)	98.0-99.5%	2.5 % max	5% max	0.7% max	5-7	5.0-6.0 mpa.s
Polyvinyl Alcohol 10-98 (L)	98.0-99.0%	2.5 % max	5% max	0.7% max	5-7	9.0-13.0 mpa.s
Polyvinyl Alcohol 10-99 (L)	99.0-99.9%	2.5 % max	5% max	0.7% max	5-7	9.0-13.0 mpa.s
Polyvinyl Alcohol 13-88 (L)	86.0-90.0%(mol/mol)	2.5 % max	5% max	0.7% max	5-7	11.0-14.0 mpa.s
Polyvinyl Alcohol 14-92 (L)	90.0-94.0%	2.5 % max	5% max	0.7% max	5-7	13.0-18.0 mpa.s
Polyvinyl Alcohol 17-88 (L)	86.0-90.0%	2.5 % max	5% max	0.7% max	5-7	20.0-28.0 mpa.s
Polyvinyl Alcohol 17-98 (L)	98.0-99.0%	2.5 % max	5% max	0.7% max	5-7	25.0-32.0 mpa.s
Polyvinyl Alcohol 17-99 (L)	99.0-99.9%	2.5 % max	5% max	0.7% max	5-7	22.0-30.0 mpa.s
Polyvinyl Alcohol 20-88 (L)	86.0-90.0%	2.5 % max	5% max	0.7% max	5-7	28.0-35.0 mpa.s
Polyvinyl Alcohol 20-99 (L)	98.0-99.9%	2.5 % max	5% max	0.7% max	5-7	32.0-42.0 mpa.s
Polyvinyl Alcohol (L)	86.0-90.0%	2.5 % max	5% max	0.7% max	5-7	40.0-50.0 mpa.s
Polyvinyl Alcohol 24-99 (L)	99.0-99.9%	2.5 % max	5% max	0.7% max	5-7	50.0-60.0 mpa.s
Polyvinyl Alcohol 26-88 (L)	86.0-90.0%	2.5 % max	5% max	0.7% max	5-7	50.0-60.0 mpa.s
Polyvinyl Alcohol 26-99 (L)	99.0-99.9%	2.5 % max	5% max	0.7% max	5-7	60.0-75.0 mpa.s
Polyvinyl Alcohol 22-99 (H)	99.0-99.9%	7.0 % max	8.0% max	3.0% max	5-7.5	32.0-42.0 mpa.s
Polyvinyl Alcohol 20-99 (H)	99.0-99.9%	7.0 % max	8.0% max	3.0% max	5-7.5	32.0-42.0 mpa.s
Polyvinyl Alcohol 17-92 (L)	90.0-94.0%	2.5 % max	5% max	0.7% max	5-7	28.0-32.0 mpa.s
Polyvinyl Alcohol 17-92 (L)	90.0-94.0%	2.5 % max	5% max	0.7% max	5-7	20.0-26.0 mpa.s
Polyvinyl Alcohol 30-99 (L)	99.0-99.9%	2.5 % max	5% max	0.7% max	5-7	80.0-100.0 mpa.s